

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
3 October 2002 (03.10.2002)

PCT

(10) International Publication Number
WO 02/077081 A1(51) International Patent Classification:
C08K 5/3437, C08L 29/14, C09B 5/62 C08J 5/18,(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(21) International Application Number: PCT/US02/08687

(22) International Filing Date: 22 March 2002 (22.03.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/278,096 23 March 2001 (23.03.2001) US(71) Applicant: SOLUTIA, INC. [US/US]; 575 Maryville
Centre, St. Louis, MO 63141-3141 (US).(84) Designated States (*regional*): ARIPO patent (GH, GM, KB, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CR, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:


- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(72) Inventors: GARRETT, Paul, D.; 15 Allen Road, Sturbridge, MA 01566 (US). BOEHM, Arno; Kirchwaldstr. 75, 68305 Mannheim (DE). BOOTH, Howard, D., Jr.; 34 Gloria Drive, Westfield, MA 01085 (US).

(74) Agents: MANDRA, Raymond, R. et al.; Fitzpatrick, Cella, Harper and Scinto, 30 Rockefeller Plaza, New York, NY 10112-3800 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CONTROLLING SOLAR RADIATION IN SAFETY GLASS LAMINATES



(57) Abstract: Plasticized polyvinyl butyral sheet containing dispersed therein, an infrared-absorbing effective amount of at least one quaternarylenetetracarboxylic diimide infrared-absorbing additive of formula I in the specification. A glass laminate having visible light transmitting and infrared light absorbing properties contains such sheet sandwiched between glass layers.

WO 02/077081 A1

WO 02/077081

PCT/US02/08687

- 1 -

TITLE

CONTROLLING SOLAR RADIATION IN SAFETY GLASS LAMINATES

5

10 BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to plasticized polyvinyl butyral
15 (PVB) sheet containing dispersed heat absorbing additives
and to a glass laminate containing such sheet,

Related Background Art

20 Laminated safety glass containing shock-dissipating sheet
of plasticized PVB between two glass layers is widely used
in vehicle and building windows where the PVB sheet

WO 02/077081

PCT/US02/08687

-2-

functions to absorb the blow from the head of an occupant within a vehicle containing the window or from a foreign object from outside the window without penetrating the safety glass laminate. It is also known to disperse minor quantities of functional additives in the PVB sheet formulation to selectively absorb heat-producing infrared (IR) solar radiation while not hampering the transmission of visible light through the glass laminate containing such PVB sheet. With sheet containing such additives, excessive heating and physical damage to an interior area surrounded by the laminated glass (such as the interior of a vehicle parked in the sun) is thus avoided. In this regard, U.S. Patent No. 5,830,568, discloses inorganic and organic IR-absorbing additives in PVB sheet in a layered safety glass laminate.

U.S. Patent Nos. 5,405,962 and 5,986,099, disclose quaterrylenetetra-carboxylic diimide compounds and their preparation. The '962 patent discloses use of non-core substituted quaterrylene compounds as pigments or fluorescent dyes or as photoconductors. Uses for the core substituted diimide compounds of the '099 patent are disclosed also as pigments or fluorescent dyes particularly for coloring organic materials or organic/inorganic composites.

A need continues to exist for improvements in the art of selectively controlling solar radiation in safety glass laminates by means of the composition of the PVB sheet in such laminates.

WO 02/077081

PCT/US02/08687

- 3 -

SUMMARY OF THE INVENTION

Now improvements have been made in the composition of PVB sheets containing additives for selectively controlling
5 solar radiation.

Accordingly, a principal object of this invention is to provide IR-heat absorbing and visible light transmitting properties in glass laminates where heat blocking is
10 achieved by the formulation of the PVB sheet per se without requiring additional functional layers in the laminate to accomplish this, i.e., on the surfaces of either the glass layer(s) or by incorporation of specially coated films within the laminate.

15 A specific object is to provide plasticized PVB sheet containing one or more organic IR-absorbing additives which can be combined with glass in a safety glass laminate to provide improved heat insulating properties.


20 Other objects will in part be obvious and will in part appear from the following description and claims.

These and other objects are accomplished by providing
25 plasticized polyvinyl butyral sheet containing an infrared-absorbing effective amount of at least one quaterstylenetetracarboxylic diimide of formula I:

WO 02/077081

PCT/US02/08687

- 4 -



wherein

R and R' are independently C₁-C₃₀-alkyl whose carbon chain
 5 optionally is interrupted by one or more of -O-, -S-,
 -NR¹-, -CO- and/or -SO₂- and which optionally is
 monosubstituted or polysubstituted by cyano, C₁-C₆-alkoxy
 or a 5-, 6- or 7-membered heterocyclic radical which is
 attached via a nitrogen atom and which optionally contains
 10 additional heteroatoms and optionally is aromatic;

C₁-C₆-cycloalkyl whose carbon chain may be interrupted by
 one or more groups selected from the group consisting of -
 O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be
 15 monosubstituted or polysubstituted by C₁-C₆-alkyl; or

aryl or hetaryl, each of which optionally is
 monosubstituted or polysubstituted by C₁-C₁₈-alkyl,
 C₁-C₆-alkoxy, cyano, -CONER², -NECOR² and/or aryl- or
 20 hetarylazo, each of which optionally is substituted by
 C₁-C₁₀-alkyl, C₁-C₆-alkoxy or halogen, where

R¹ is hydrogen or C₁-C₆-alkyl; and


WO 02/077081

PCT/US02/08687

- 5 -

R^2 is hydrogen; C_1 - C_{18} -alkyl; aryl or hetaryl, each of which optionally is substituted by C_1 - C_6 -alkyl, C_1 - C_6 -alkoxy, halogen or cyano;

- 5 X is independently halogen; C_1 - C_{18} -alkyl, aryloxy, arylthio, hetaryloxy or hetarylthio, each of which may be substituted by C_1 - C_4 -alkyl, or C_1 - C_{18} -alkoxy; or



10

where

15

R^3 is C_1 - C_8 -alkyl, whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1 - C_6 -alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic; or

20

C_5 - C_8 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1 - C_6 -alkyl;

25 and p is from 0-16.


In a particularly preferred embodiment of the invention the quaterylene-tetracarboxylic diimide is a tert-

WO 02/077081

PCT/US02/08687

- 6 -

alkylphenoxy-substituted quaterrylene-tetracarboxylic diimide infrared-absorbing additive of formula II:



5

where

Q is a N,N'-disubstituted quaterrylene-3,4:13,14-tetracarboxylic diimide radical as described above;

10

R³ is the same as defined above;

Hal is chloro and/or bromo;

15 m is from 0 to 15; and

n is from 1 to 16, subject to the proviso that the sum m + n is ≤ 16.

20 The PVB sheet of this invention may also include one or more inorganic IR-absorbing additives such as nanoparticulate lanthanum hexaboride, antimony tin oxide, indium tin oxide and mixtures thereof. Colorants, e.g., pigments and dyes, UV stabilizers and adhesion control
25 agents may also be included in the PVB sheet of this invention.

WO 02/077081

PCT/US02/08687

-7-

This invention is also directed to a laminate having two glass sheets with the above-described PVB sheet disposed therebetween. The laminate of this invention may also include two or more PVB sheets interposed between the glass sheets. For example, a laminate may have one PVB sheet containing an IR absorbing effective amount of quaternarylimide and a second PVB sheet containing one or more of an inorganic IR-absorbing additive. In addition, the laminates of this invention may include a functional PET film interposed between two sheets of PVB so long as the quaternarylimide present in either one PVB sheet alone or both PVB sheets together is an IR absorbing effective amount of quaternarylimide.

15 BRIEF DESCRIPTION OF THE DRAWING

In describing the overall invention, reference will be made to the accompanying drawing which is a plot of intensity versus wavelength of solar radiation passing through a glass laminate of the invention containing PVB sheet of the invention.

DETAILED DESCRIPTION OF THE INVENTION

25 The quaternarylenetetra-carboxylic diimide (hereinafter sometimes called "quaternarylimide") IR-absorber for incorporation as an additive into the formulation of PVB sheet according to this invention is of formula I.

WO 02/077081

PCT/US02/08687

- 8 -

A particularly preferred IR-absorber is the tert-alkylphenoxy-substituted quaterrylenetetracarboxylic diimide (hereinafter sometimes called "tert-alkylphenoxy-substituted quaterrylimide") described by formula II:

5

The tert-alkylphenoxy radicals characterizing the compounds II and also any halogen atoms present in addition may be attached directly or via aryl substituents to the polycyclic core of the quaterrylimide. It will be appreciated that both forms of attachment can occur in one and the same compound II. If present, the aryl substituents are resistant to base attack, and include, for example, unsubstituted or alkyl- and/or alkoxy-substituted aryl, especially phenyl, or hetaryl, such as 2-, 3- and 4-pyridyl and pyrimidyl. These aryl substituents can either be attached directly to the polycyclic core or the imide nitrogen atoms. Preferably the quaterrylimides of formula II, bear the tert-alkylphenoxy radicals directly on the polycyclic core or have at least directly attached tert-alkylphenoxy radicals in addition to arylene-attached tert-alkylphenoxy radicals.

The compounds II contain from at least 1 to 16 (n: 1-16), especially 2 to 8, tert-alkylphenoxy radicals.

The compounds of II are prepared by introducing the tert-alkylphenoxy radicals into the quaterrylimides by replacement of halogen. Accordingly, if not all the halogen atoms are replaced, the compounds II can also

WO 02/077081

PCT/US02/08687

- 9 -

contain up to 15 (m: 0-15), especially from 1 to 4, halogen atoms, in which case the total number of the two substituent groups should not exceed 16, preferably 8.

- 5 Generally the range of $m+n$ for compound II will be 1-16 and preferably 2-8.

When the quaterrylimide radical contains additional aryl substituents not used for attaching tert-alkylphenoxy, the
10 maximum for the sum $m+n$ decreases accordingly, of course.

Suitable examples of the R^3 radicals appearing in formula II and also of their substituents include methyl, ethyl, propyl, isopropyl, butyl, isobutyl, tert-butyl, pentyl,
15 isopentyl, neopentyl, tert-pentyl, hexyl, 2-methylpentyl, tert-pentyl, hexyl, 2-methylpentyl, heptyl, 1-ethylpentyl, octyl, 2-ethylhexyl and isooctyl;

2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-
20 isopropoxyethyl, 2-butoxyethyl, 2- and 3-methoxypropyl, 2- and 3-ethoxypropyl, 2- and 3-propoxypropyl, 2- and 3-butoxypropyl, 2- and 4-methoxybutyl, 2- and 4-ethoxybutyl, 2- and 4-propoxybutyl, 3,6-dioxaheptyl, 3,6-dioxaoctyl, 4,8-dioxanonyl, 3,7-dioxaoctyl, 3,7-dioxanonyl, 4,7-
25 dioxaoctyl, 4,7-dioxanonyl, 2- and 4-butoxybutyl, 4,8-dioxadecyl, 3,6,9-trioxadecyl and 3,6,9-trioxaundecyl;

2-methylthioethyl, 2-ethylthioethyl, 2-propylthioethyl, 2-isopropylthioethyl, 2-butylthioethyl, 2- and 3-
30 methylthiopropyl, 2- and 3-ethylthiopropyl, 2- and 3-

WO 02/077081

PCT/US02/08687

- 10 -

propylthiopropyl, 2- and 3-butylthiopropyl, 2- and 4-methylthiobutyl, 2- and 4-ethylthiobutyl, 2- and 4-propylthiobutyl, 3,6-dithiaheptyl, 3,6-dithiaoctyl, 4,8-dithianonyl, 3,7-dithiaoctyl, 3,7-dithianonyl, 4,7-dithiaoctyl, 4,7-dithianonyl, 2- and 4-butylthiobutyl, 4,8-dithiadecyl, 3,6,9-trithiadecyl and 3,6,9-trithiaundecyl;

2-monomethyl- and 2-monoethylaminoethyl, 2-dimethylaminoethyl, 2- and 3-dimethylaminopropyl, 3-monoisopropylaminopropyl, 2- and 4-monopropylaminobutyl, 2- and 4-monomethylaminobutyl, 6-methyl-3,6-diazaheptyl, 3,6-dimethyl-3,6-diazaheptyl, 3,6-diazaoctyl, 3,6-dimethyl-3,6-diazaoctyl, 9-methyl-3,6,9-triazadecyl, 3,6,9-trimethyl-3,6,9-triazadecyl, 3,6,9-triazaundecyl and 3,6,9-trimethyl-3,6,9-triazaundecyl;

propan-2-on-1-yl, butan-3-on-1-yl, butan-3-on-2-yl and 2-ethylpentan-3-on-1-yl;

2-methylsulfonylethyl, 2-ethylsulfonylethyl, 2-propylsulfonylethyl, 2-isopropylsulfonylethyl, 2-butylsulfonylethyl, 2- and 3-methylsulfonylpropyl, 2- and 3-ethylsulfonylpropyl, 2- and 3-propylsulfonylpropyl, 2- and 3-butylsulfonylpropyl, 2- and 4-methylsulfonylbutyl, 2- and 4-ethylsulfonylbutyl, 2- and 4-propylsulfonylbutyl and 4-butylsulfonylbutyl;

WO 02/077081

PCT/US02/08687

- 11 -

methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, sec-butoxy, tert-butoxy, pentoxy, isopentoxy, neopentoxy, tert-pentoxy and hexoxy;

- 5 cyclopentyl, 2- and 3-methylcyclopentyl, 2- and 3-ethylcyclopentyl, cyclohexyl, 2-, 3- and 4-methylcyclohexyl, 2-, 3- and 4-ethylcyclohexyl, 3- and 4-propylcyclohexyl, 3- and 4-isopropylcyclohexyl, 3- and 4-butylcyclohexyl, 3- and 4-sec-butylcyclohexyl, 3- and 4-tert-butylcyclohexyl, cycloheptyl, 2-, 3- and 4-methylcycloheptyl, 2-, 3- and 4-ethylcycloheptyl, 3- and 4-propylcycloheptyl, 3- and 4-isopropylcycloheptyl, 3- and 4-butylcycloheptyl, 3- and 4-sec-butylcycloheptyl, 3- and 4-tert-butylcycloheptyl, cyclooctyl, 2-, 3-, 4- and 5-methylcyclooctyl, 2-, 3-, 4- and 5-ethylcyclooctyl, 3-, 4- and 5-propylcyclooctyl, 2-dioxanyl, 4-morpholinyl, 2- and 3-tetrahydrofuryl, 1-, 2- and 3-pyrrolidinyl and 1-, 2-, 3- and 4-piperidyl.

- 20 Examples of preferred tert-alkoxyphenoxy radicals are p-(1,1-dimethylpropyl)phenoxy, p-(1,1-dimethylbutyl)phenoxy, p-(1,1-dimethylpentyl)phenoxy, p-(1,1,3,3-tetramethylbutyl)phenoxy, p-(2-cyclopentyl-1,1-dimethylethyl)phenoxy, p-(2-cyclohexyl-1,1-dimethylethyl)phenoxy, p-(2-cycloheptyl-1,1-dimethylethyl)phenoxy and p-(1,1-dimethyl-2-(4-morpholinyl)ethyl)phenoxy.

- The quaternarylimide radicals of compound II will generally bear the following base-stable substituents on the imide

WO 02/077081

PCT/US02/08687

- 12 -

nitrogen atoms, i.e., preferably the R groups of formula I are independently:

5 C₆-C₃₀-alkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C₁-C₆-alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms
10 and be aromatic;

C₅-C₈-cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be
15 monosubstituted or polysubstituted by C₁-C₆-alkyl; or aryl or hetaryl which may be monosubstituted or polysubstituted by C₁-C₁₈-alkyl, C₁-C₆-alkoxy, cyano, -CONH-R¹ and/or -NH-COR¹.

20

The following radicals may be specifically mentioned by way of example for these substituents, i.e., as preferred R and R' groups on the imide nitrogen atoms of the quaternarylimide, in addition to the radicals already
25 mentioned:

nonyl, isononyl, decyl, isodecyl, undecyl, dodecyl, tridecyl, isotridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl and eicosyl (the
30 designations isononyl, isodecyl and isotridecyl as well as

WO 02/077081

PCT/US02/08687

- 13 -

the above mentioned designation isooctyl are trivial names derived from the alcohols obtained by the oxo process);

3,6,9-trioxadodecyl, 3,6,9,12-tetraoxatridecyl and
 5 3,6,9,12-tetraoxatetradecyl; 3,6,9-trithiadodecyl,
 3,6,9,12-tetrathiatridecyl and 3,6,9,12-
 tetrathiatetradecyl;

carbamoyl, methylaminocarbonyl, ethylaminocarbonyl,
 10 propylaminocarbonyl, butylaminocarbonyl,
 pentylaminocarbonyl, hexylaminocarbonyl,
 heptylaminocarbonyl, octylaminocarbonyl,
 nonylaminocarbonyl and decylaminocarbonyl; formylamino,
 acetylamino and propionylamino;

15 2-, 3- and 4-methylphenyl, 2,4-, 2,5-, 3,5- and 2,6-
 dimethylphenyl, 2,4,6-trimethylphenyl, 2-, 3- and 4-
 ethylphenyl, 2,4-, 2,5-, 3,5- and 2,6-diethylphenyl,
 2,4,6-triethylphenyl, 2-, 3- and 4-propylphenyl, 2,4-,
 20 2,5-, 3,5- and 2,6-dipropylphenyl, 2,4,6-tripropylphenyl,
 2-, 3- and 4-isopropylphenyl, 2,4-, 2,5-, 3,5- and 2,6-
 diisopropylphenyl, 2,4,6-triisopropylphenyl, 2-, 3- and 4-
 butylphenyl, 2,4-, 2,5-, 3,5- and 2,6-dibutylphenyl,
 2,4,6-tributylphenyl, 2-, 3- and 4-isobutylphenyl, 2,4-,
 25 2,5-, 3,5- and 2,6-diisobutylphenyl, 2,4,6-
 triisobutylphenyl, 2-, 3- and 4-sec-butylphenyl, 2,4-,
 2,5-, 3,5- and 2,6-di-sec-butylphenyl, 2,4,6-tri-sec-
 butylphenyl, 2-, 3- and 4-tert-butylphenyl, 2,4-, 2,5-,
 3,5- and 2,6-di-tert-butylphenyl and 2,4,6-tri-tert-
 30 butylphenyl; 2-, 3- and 4-methoxyphenyl, 2,4-, 2,5-, 3,5-

WO 02/077081

PCT/US02/08687

- 14 -

and 2,6-dimethoxyphenyl, 2,4,6-trimethoxyphenyl, 2-, 3-
 and 4-ethoxyphenyl, 2,4-, 2,5-, 3,5- and 2,6-
 diethoxyphenyl, 2,4,6-triethoxyphenyl, 2-, 3- and 4-
 propoxyphenyl, 2,4-, 2,5-, 3,5- and 2,6-dipropoxyphenyl,
 5 2-, 3- and 4-isopropoxyphenyl, 2,4-, 2,5-, 3,5- and 2,6-
 diisopropoxyphenyl and 2-, 3- and 4-butoxyphenyl; 2-, 3-
 and 4-cyanophenyl; 3- and 4-carboxamidophenyl, 3- and 4-N-
 (methyl)carboxamidophenyl and 3- and 4-N-
 (ethyl)carboxamidophenyl; 3- and 4-acetylaminophenyl, 3-
 10 and 4-propionylaminophenyl and 3- and 4-
 butyrylaminophenyl.


The preparation of various quaterrylenetetracarboxylic
 diimides is described in U.S. Patent No. 5,405,962 and
 15 U.S. Patent No. 5,986,099, the disclosure of both of which
 are incorporated by reference herein. The tert-
 alkylphenoxy substituted quaterrylimides of formula II may-
 be prepared by reacting the corresponding halides of the
 formula III

20



with tert-alkylphenols of the formula IV

25



WO 02/077081

PCT/US02/08687

- 15 -

in an inert basic nitrogen-containing solvent in the presence of a base and if desired subsequently removing unwanted halogen.

- 5 Useful inert basic nitrogen-containing solvents are in particular polar solvents, especially nitrogen-containing heterocycles, such as pyridine, pyrimidine, quinoline, isoquinoline, quinaldine and preferably N-methylpyrrolidone, and also carboxamides, such as N,N-
- 10 dimethylformamide and N,N-dimethylacetamide.

The solvent quantity depends on the solubility of the halide III and is customarily in the range from 2 to 40 g, preferably from 4 to 25 g, of solvent per g of halide III.

15

- Useful bases are in particular nonnucleophilic or only weakly nucleophilic compounds. Examples of such bases are alkali metal hydroxides, such as potassium hydroxide and sodium hydroxide, alkali metal carbonates, such as
- 20 potassium carbonate and sodium carbonate, and also alkali metal alkoxides of tertiary alcohols, such as lithium tert-butoxide, sodium tert-butoxide and potassium tert-butoxide, which are used in anhydrous form.

- 25 In general, from 0.8 to 1.5, preferably from 1.0 to 1.2, molar equivalents of base are used per mole of halogen atom to be replaced.

- The halides III used as starting materials are generally
- 30 known or obtainable according to known methods by reacting

WO 02/077081

PCT/US02/08687

- 16 -

the unhalogenated quaterrylimide with halogenating agents, especially the elemental halogens. Such halides III that contain halogen atoms attached to aryl substituents are known to be generally obtainable by introduction of the
5 halogenated aryl radicals into the polycyclic system of the quaterrylimide.

The molar ratio of halide III to phenol IV depends on the number of halogen atoms to be replaced. In general, from
10 1 to 2, preferably from 1 to 1.3, mol of phenol IV is used per mole of halogen atom to be replaced in halide III.

The reaction temperature is customarily in the range from 50 to 200°C, preferably at from 60 to 140°C.

15

It is advisable for the reaction to be carried out under protective gas, for example nitrogen or argon.

The reaction time depends on the reactivity of the halide
20 III and is about 2-48 h.

Varying the reaction conditions - amount of phenol IV and base and the reaction temperature - advantageously provides control over the halogen replacement, so that it
25 is no problem to prepare not only compounds II where all the halogen atoms have been replaced ($m=0$) but also compounds II which do contain halogen. If desired, the halogen can subsequently be removed from the compound II. Thus, a single starting material III can be used, if
30 desired, to prepare various compounds II.

WO 02/077081

PCT/US02/08687

- 17 -

The process is advantageously carried out by initially charging the solvent, adding halide III, phenol IV and base and heating the resulting solution or suspension to the desired reaction temperature for 2-48 h while stirring
5 under protective gas.

After cooling down to room temperature, the reaction product can be isolated by filtering off the precipitated reaction product directly or after dilution with 3 to 4
10 times the volume of water, a dilute inorganic acid, for example 5-10% by weight hydrochloric acid, or an aliphatic alcohol, for example methanol, washing first with a little solvent and then with water to neutral run-off and drying under reduced pressure.

15 In some cases, especially in order to obtain high degrees of substitution or in the case of the bromides III, which are more base-labile and hence more prone to undesirable secondary reactions, it can be advantageous for high
20 product purity for the phenoxylation reaction to be carried out in two stages. In this case, the halide III is initially reacted with only a portion, advantageously the amount needed to replace the most labile halogen substituents, of phenol IV and base, the partially
25 phenoxyolated product is separated from the reaction mixture by filtration and is subsequently reacted with the rest of phenol IV and base to form the desired product.

In general, the compounds II obtained as described above
30 have a sufficiently high assay (> 95%) that there is no

WO 02/077081

PCT/US02/08687

-18-

need for further purification. Analytically pure products can be prepared by recrystallization from aromatic solvents, such as toluene and xylene, or halogenated hydrocarbons, such as methylene chloride and chloroform, 5 or by filtration of a solution of the products in these solvents through silica gel and subsequent concentrating.

If only part of the halogen substituents were replaced and the halogen still present is to be removed, this can be 10 done by means of known methods.

By way of example, two dehalogenations will now be 15 described which would be very advantageous for this purpose.

In the first method, the dehalogenation is base-induced in the presence of an inert basic nitrogen-containing or 20 aromatic solvent.

Useful bases for this purpose include for example alkali metal hydroxides, such as potassium hydroxide and sodium hydroxide, alkali metal carbonates, such as potassium 25 carbonate and sodium carbonate, alkali metal alkoxides of secondary and tertiary alcohols such as lithium isopropoxide, sodium isopropoxide, potassium isopropoxide, lithium tert-butoxide, sodium tert-butoxide and potassium tert-butoxide, and also sterically hindered nitrogen

WO 02/077081

PCT/US02/08687

- 19 -

bases, such as diazabicyclooctane (DABCO),
diazabicyclononene (DBN) and diazabicycloundecene (DBU).

The amount of base is not critical as such. It is
5 customary to use from 1 to 3, preferably from 1 to 1.5,
mol equivalents of base per mole of halogen atom to be
eliminated.

Useful solvents include not only aromatic solvents, such
10 as toluene and xylene, but also the same solvents as used
in the phenoxylation, the use level of which in turn
depends on the solubility of the compound I to be
dehalogenated and is generally in the range from 2 to 50
g, preferably in the range from 5 to 25 g, per g of
15 compound I.

The reaction temperature is customarily in the range from
50 to 200°C, preferably from 60 to 130°C.

20 It is advisable for the dehalogenation to be carried out
under protective gas, for example nitrogen or argon.

The reaction time depends on the reactivity of the
compound I to be dehalogenated and is about 1-6 h.

25

The process is advantageously carried out by initially
charging a solution or suspension in the solvent of the
compound I to be dehalogenated, adding the base and
heating the resulting mixture to the desired reaction
30 temperature for 1-6 h while stirring under protective gas.

WO 02/077081

PCT/US02/08687

- 20 -

When there is a risk of undesirable secondary reactions, for example saponifications, it is advantageous for the base not to be added until after heating to reaction temperature.

5

After cooling down to room temperature, the reaction product can be isolated by diluting the reaction mixture with from 3 to 4 times the volume of a dilute inorganic acid, for example 5-10% by weight hydrochloric acid, filtering off the thusly precipitated product, washing initially with the dilute acid and then with methanol or water to neutral run-off and drying under reduced pressure.

15 The second method comprises a transition metal catalyzed reductive dehalogenation in the presence of a solvent that is inert under the reaction conditions.

The reducing agents used here are preferably complex hydrides, especially aluminohydrides, such as lithium aluminohydride, and especially borohydrides, preferably sodium borohydride, or elemental hydrogen.

The amount of reducing agent is not critical as such. Generally from 1 to 5, preferably from 2 to 3, mol equivalents of reducing agent are used per mole of halogen atom to be eliminated.

Useful transition metal catalysts include in particular palladium compounds, such as Pd(II) and Pd(0) compounds.

30

WO 02/077081

PCT/US02/08687

- 21 -

The reduction with complex hydrides is preferably catalyzed using palladium(II) acetate, di-chloro(1,5-cyclooctadiene)palladium(II), dichloro[1,1'-bis(diphenylphosphino)ferrocene]palladium(II),
5 tris(dibenzylideneacetone)dipalladium(0), tetrakis(triphenylphosphine)palladium(0) and tetrakis(tris-o-tolylphosphine)palladium(0) and the reduction with elemental hydrogen is preferably catalyzed using palladium-doped activated carbon.

10

Generally from 0.5 to 2 mol% of catalyst are used per mole of halogen atom to be eliminated.

15

The choice of solvent depends on the choice of reducing agent. When complex hydrides are used, it is especially polar aprotic solvents, such as aliphatic and cycloaliphatic ethers, aromatic solvents and aliphatic nitriles, which are suitable, while it is especially aliphatic alcohols which are suitable if elemental
20 hydrogen is used.

20

Specific examples of these solvents are diethyl ether, tetrahydrofuran and dioxane, toluene and xylene, acetonitrile, which is used with borohydrides in
25 particular, and also methanol and ethanol.

25

The amount of solvent is determined by the solubility of the compound I to be dehalogenated and is generally in the range from 2 to 50 g, preferably in the range from 5 to 25
30 g, per g of compound I.

30

WO 02/077081

PCT/US02/08687

- 22 -

The reaction temperature is customarily in the range from 0 to 150°C, preferably in the range from 20 to 100°C, although the reduction with complex hydrides is generally carried out at higher temperatures (about 50-100°C) than
5 the reduction with elemental hydrogen.

When complex hydrides are used as reducing agents, it is advisable to work under protective gas. A hydrogenation with elemental hydrogen is advantageously performed under
10 a small hydrogen overpressure.

Depending on the reactivity of compound I, the dehalogenation takes from 4 to 72 h.

15 The process for dehalogenating with complex hydrides is advantageously carried out by initially charging the solvent, adding the compound I to be dehalogenated and subsequently the hydride and the catalyst, and heating the resulting solution or suspension to the desired reaction
20 temperature for 4-72 h while stirring under protective gas.

After cooling down to room temperature and destroying excess hydride by addition of water, the reaction product
25 can be isolated as described for the base-induced dehalogenation.

The process for dehalogenating with elemental hydrogen is carried out by initially charging a hydrogenation reactor
30 with a suspension, in the solvent, of the compound I to be

WO 02/077081

PCT/US02/08687

- 23 -

dehalogenated and the catalyst and heating to the reaction temperature for 4-72 h while stirring under a small hydrogen overpressure (about 0.1-0.5 bar).

- 5 After cooling down to room temperature, depressurizing and displacing excess hydrogen with nitrogen, the reaction product can be isolated as already described.

- To produce compounds I having a > 95% assay, the
10 as-dehalogenated compounds can be subjected to a purification step. Useful purification options include for example fractional crystallization from solvent mixtures with an aromatic solvent, such as toluene and xylene, or a halogenated hydrocarbon, such as methylene
15 chloride, chloroform and 1,1,2,2-tetrachloroethane, as one component and an extremely nonpolar solvent, such as pentane or hexane, as the other component or column chromatography over silica gel using these solvent mixtures as mobile phase.

20

- The quaterrylimide IR-absorber of formula I, and more preferably the tert-alkyphenoxy-substituted quaterrylimide IR-absorber of formula II, in solid form is incorporated into the formulation of the PVB sheet by first adding it
25 as powder to liquid plasticizer for the PVB sheet with stirring at about 50°C after which the stirred mixture along with any other sheet property-influencing additives, is combined with PVB resin to form a premix which is melted and homogenized in an intensive mixer and then
30 shaped into sheet form.

WO 02/077081

PCT/US02/08687

- 24 -

The concentration of the quaterrylimide will vary depending on the application of the laminate, e.g. windscreen or architectural glass, target transmission range, PVB thickness and glass thickness. The glass

5 thickness for architectural application will typically range from about 4.8 mm (3/16 inch) to about 12.7 mm (1/2 inch), and from about 1.6 mm to about 2.5 mm for a windscreen application. More particularly, for example, for a laminate having a PVB thickness of about 0.76 mm and

10 a glass thickness of about 6 mm that is used as architectural glass, the quaterrylimide will generally be present in the PVB in an amount of about 0.003 to about 0.1 percent by weight, preferably about 0.005 to about 0.08 percent by weight, and most preferably 0.01 to about

15 0.06 percent by weight of the PVB. In general, a PVB layer used in a laminate for windscreen application will have lower concentrations of quaterrylimide than a PVB layer used in an architectural glass application due to regulations on visible transmittance for laminated

20 automotive windscreens. For example, for a laminate having the PVB thickness of about 0.76 mm and a glass thickness of about 2.1 mm used as a windscreen, the quaterrylimide will generally be present in the PVB in an amount of about 0.003 to about 0.07 percent by weight,

25 preferably about 0.005 to about 0.06 percent by weight, and most preferably about 0.01 to about 0.05 percent by weight of the PVB.

The particular quaterrylimide used in the PVB sheet of

30 this invention should be compatible with the PVB, stable

WO 02/077081

PCT/US02/08687

-25-

and have appropriate IR absorbing characteristics. Referring to formula I, it is generally believed that R has little influence on absorption wavelength, but has a strong influence on solubility, aggregation behavior and stability. For example, if R is short chain alkyl the quaternarylimide will have low solubility, a tendency to aggregation and high chemical and thermal stability. If R is longer chain alkyl, cycloalkyl, or unsubstituted phenyl, then the solubility will be much higher and the aggregation tendency low, but stability will be lower. Preferably, R is substituted phenyl or higher aryl or heteraryl. In this case the quaternarylimide will generally have high solubility, low aggregation tendency, strong sharp adsorption bands and high chemical and thermal stability.

The X group of formula I is believed to influence both absorption and compatibility, with generally little influence on thermal or chemical stability unless X is halo or (het)arylthio. For example, if X is hydrogen there is generally little influence on solubility or absorption, while if X is alkyl or alke(i)nyl this results in a slight enhancement of solubility and a small bathochromic shift in absorption wavelength. If X is halogen, this will result in a hypsochromic shift in absorption wavelength (to about 740-750 nanometers), while if X is (het)aryloxy this will cause a strong bathochromic shift of up to 35 nanometers, high chemical stability and a moderate enhancement of solubility without substitution or a strong enhancement of solubility with substitution on

WO 02/077081

PCT/US02/08687

-26-

the (het)aryl moiety. If X is (het)arylthio, an even stronger bathochromic shift in absorption wavelength is expected than with (het)aryloxy, but the resulting quaternarylimide is likely to have reduced chemical and thermal stability. The above described effects caused by the selection of X will be more pronounced as p of formula I is made larger.

As previously noted, the PVB sheet of this invention may also contain an inorganic IR-absorber. Exemplary inorganic IR-absorbers are described in U.S. Patent No. 5,830,568, the disclosure of which is incorporated by reference herein. Such absorbers include antimony tin oxide and indium tin oxide. Other useful inorganic IR-absorbers are metal hexaborides, such as lanthanum hexaboride, which are described in EP-A-1008564. The amount of inorganic IR-absorber added to the PVB will vary with the inorganic IR-absorber employed. For example, if indium tin oxide is used it will typically be present in a range of about 0.01 to 1.0 percent by weight of PVB, while antimony tin oxide will generally be present in a range of about 0.05 to about 1.5 percent by weight of PVB.

The preparation and physical properties of these inorganic IR-absorbers in solid powder form, their dispersion in the PVB sheet and the preparation of glass laminate containing such sheet are disclosed in Japanese Patent Application (Kokai) No. 8-217500. Briefly, to desirably promote visible light (wavelength 400 to 700 nm) transparency in the finished glass laminate, particles of the inorganic

WO 02/077081

PCT/US02/08687

- 27 -

IR-absorber are 0.1 micrometer (μm) in diameter or less, preferably not greater than 0.02 μm . To minimize or avoid undesirable agglomeration of the inorganic IR additive particles which causes undesirable haze in the finished glass laminates, the particles are initially mixed with a macromolecular surfactant before dispersing in the plasticizer of the PVB sheet formulation.

The PVB sheet of this invention may also contain colorants such as dyes and pigments. The colorant may be admixed with the PVB or printed on the surface of the PVB sheet such as disclosed in U.S. Patent No. 3,922,456 and U.S. Patent No. 3,982,984. An exemplary pigment is copper phthalocyanine pigment blue available from Sigma-Aldrich Corp., St. Louis, MO. An exemplary dye that may be used is C.I. solvent blue 102, available as "KEYSTONE BLUE RC" from Keystone Aniline Corp., Chicago, IL.

Using the CIELAB system, a well known international standard for color measurement, the color of an object under fixed viewing conditions can be defined. A set of dimensionless coordinates L^* , a^* , b^* are used to define a color's hue and intensity. These coordinates are measured according to instructions provided in the publication "Standard Practice for Computing the Colors of Objects by Using the CIE System," ASTM E 308-01. The wave-length range is between 400 nm and 700 nm, at a wavelength interval of 20 nm. The coordinate L^* is used to measure the lightness or darkness of a color. White is denoted by $L^*=100$ and black is denoted by $L^*=0$. The coordinate a^*

WO 02/077081

PCT/US02/08687

-28-

measures the level of green or red color in the object, and the coordinate b^* measures the level of blue or yellow in the object.

- 5 In a preferred embodiment, the colorants that are included produce a green color in the PVB sheet. The PVB sheet is typically placed between glass sheets forming a laminate. The color of the green colored PVB sheet or green colored laminate is defined by the CIELAB system, where L^* is from
10 about 76.0 to about 94.0, a^* is from about -38.0 to about -8.0, and b^* is from about -5.0 to about 7.0. Preferably, the green colored PVB sheet or green colored laminate has an L^* value from about 86.0 to about 89.5, an a^* value from about -28.0 to about -15.0, and a b^* value from about
15 -1.0 to about 4.5.

- In another preferred embodiment, a gray color is produced by including the colorants in the PVB sheet. The gray colored PVB sheet or gray colored laminate formed by
20 placing the gray colored PVB sheet between glass sheets has an L^* value from about 59.0 to about 87.0, an a^* value from about -7.0 to about 3.0, and a b^* value from about -8.0 to about 2.0. More preferably, the gray colored PVB sheet or gray colored laminate has an L^* value from about
25 69.5 to about 77.0, an a^* value from about -4.0 to about 1.0, and a b^* value from about -5.0 to about 0.5.

- PVB resin of the sheet of this invention has a weight average molecular weight greater than 70,000, preferably
30 about 100,000 to 250,000, as measured by size exclusion

WO 02/077081

PCT/US02/08687

- 29 -

chromatography using low angle laser light scattering. On a weight basis PVB typically comprises less than 19.5%, preferably about 17 to 19% hydroxyl groups calculated as polyvinyl alcohol (PVOH); 0 to 10%, preferably 0 to 3% residual ester groups, calculated as polyvinyl ester, e.g. acetate, with the balance being acetal, preferably butyraldehyde acetal, but optionally including a minor amount of acetal groups other than butyral, for example 2-ethyl hexanal as disclosed in U.S. 5,137,954.

10

PVB resin is commercially available as Butvar® resin from Solutia, Inc. of St. Louis, Mo.

The PVB resin of the sheet of this invention is typically plasticized with about 20 to 80, more commonly 25 to 45, parts plasticizer per hundred parts resin. Plasticizers commonly employed are esters of a polybasic acid or a polyhydric alcohol. Suitable plasticizers are triethylene glycol di-(2-ethylbutyrate), triethylene glycol di-(2-ethylhexanoate), triethylene glycol diheptanoate, tetraethylene glycol diheptanoate, dihexyl adipate, dioctyl adipate, hexyl cyclohexyladipate, mixtures of heptyl and nonyl adipates, diisononyl adipate, heptylnonyl adipate, dibutyl sebacate, polymeric plasticizers such as oil-modified sebacic alkyds, and mixtures of phosphates and adipates as disclosed in U.S. No. 3,841,890 and adipates such as disclosed in U.S. No. 4,144,217. Also mixed adipates made from C₄ to C₈ aldyl alcohols and cyclo C₄ to C₁₀ alcohols as disclosed in U.S. No. 5,013,779. C₆ to C₈ adipate esters such as hexyl adipate and triethylene

30

WO 02/077081

PCT/US02/08687

- 30 -

glycol di-(2-ethylhexanoate) are preferred plasticizers.

Plasticized PVB sheet at a noncritical thickness of about 0.13 to 1.3 mm is formed by preferably (in commercial systems) extruding the mixed formulation through a sheet die, i.e. forcing molten, plasticized PVB through a horizontally long vertically narrow die opening substantially conforming in size to the sheet being formed, or by casting molten polymer issuing from an extrusion die onto a die roll in close proximity to the die exit to impart desired surface characteristics to one side of the polymer. When the roll surface has minute peaks and valleys, the side of the sheet contacting the roll will have a rough surface generally conforming to the valleys and peaks. Roughness on the other side can be provided by the design of the extrudate die opening as shown, for example, in Fig. 4 of U.S. No. 4,281,980. Other known techniques for producing a rough surface on one or both sides of an extruding sheet involve specifying and controlling one or more of the following: polymer molecular weight distribution, water content and temperature of the melt. These techniques are disclosed in U.S. Nos. 2,904,844; 2,909,810; 3,994,654; 4,575,540 and European Patent No. 0185,863. Embossing downstream of the extrusion die also roughens the sheet surface. As known, this roughness is temporary to facilitate deairing during laminating after which elevated temperature and pressure during bonding of the sheet to glass melts it smooth. Lamination to glass is according to generally known procedures.

WO 02/077081

PCT/US02/08687

- 31 -

The PVB sheet of this invention preferably also contains ultraviolet light stabilizers. If used, the ultraviolet (UV) stabilizer will generally be present in a range of about 0.01 to 1.0 percent by weight of the PVB. The preferred amount of UV stabilizer will vary depending on the stabilizer employed. For example, "TINUVIN 328" available from Ciba Speciality Chemicals, Basel, Switzerland has been found to perform particularly well at a concentration of about 0.5 percent by weight of the PVB.

The sheet of the invention optionally contains other additives in addition to those defined above to enhance various performance properties; these include antioxidants, adhesion control salts and the like.

As noted previously, this invention is also directed to a laminate of two sheets of glass having the PVB sheet of this invention disposed therebetween. The sheets of glass may be any type of glass so long as it allows for visible light transmission. Such glass includes typical clear soda-lime glass, IR-reflective coated glass or IR-absorbing glass, which are well known. See e.g., U.S. Patent No. 3,944,352 and U.S. Patent 3,652,303, the disclosures of both of which are incorporated by reference. IR-absorbing glass is commercially available from PPG Industries, Inc., Pittsburgh, PA as "SOLARGREEN" glass and Pilkington PLC, St. Helens, UK as "OPTIKOOL" glass. It is also possible to place IR reflective films on the outer surface of one or both of the sheets of glass used in the laminate.

WO 02/077081

PCT/US02/08687

- 32 -

The laminate of this invention may include more than one sheet of PVB disposed between the two sheets of glass so long as the total amount of quaterrylimide in either one sheet of PVB alone or in a plurality of PVB sheets is an
5 IR-absorbing effective amount of quaterrylimide. It should be apparent that if a plurality of PVB sheets are used only one need contain the quaterrylimide. A laminate may contain a sheet of PVB containing quaterrylimide and a second sheet containing at least one inorganic IR-absorber
10 such as previously described. In yet another embodiment of this invention the laminate may include an IR-reflective layer such as IR-reflective polyethylene terephthalate (PET) layer. IR-reflective PET films in PVB laminates are described in U.S. Patent No. 5,932,329
15 and U.S. Patent No. 5,091,258, the disclosure of both of which are incorporated by reference herein. Preferably the IR-reflective PET film will be disposed between two PVB sheets. An exemplary IR reflective coated PET film is "XIR"-75 from Southwall Technologies, Inc., Palo Alto, CA.

20

Preparation of laminates of two glass substrates with one or more PVB sheet inner layers is well known to those skilled in the art.

25 Another embodiment of this invention is directed to post applied film products for visible transparent substrates, wherein the film product contains an infrared-absorbing effective amount of at least one quaterrylenetetra-carboxylic diimide of formula I. The
30 post applied film product of this invention may be applied

WO 02/077081

PCT/US02/08687

- 33 -

to architectural or automotive glass for solar infrared control or may be applied to display devices as a means of limiting the infrared output of such display devices.

- 5 In addition to the quaterxylenetetra-carboxylic diimide of formula I, at a minimum, the film product of this invention is comprised of at least one film substrate and a post application adhesive layer disposed on a surface of said film substrate to provide adhesion of the film
- 10 product to a visibly transparent glass substrate. The film product may also include a plurality of film substrates that have disposed therebetween a laminating adhesive. The film product of this invention may also include one or more protective coatings disposed on the
- 15 outer surface of the film substrate. As used herein the outer surface of the film product is that which faces in a direction opposite of the surface of the film product having the post application adhesive layer thereon.
- 20 The quaterxylenetetra-carboxylic diimide of formula I may be incorporated in one or more of the film substrate, the post application adhesive layer or when present, the laminating adhesive and/or protective coating of the film product. Typically, the film substrate used in the film
- 25 product of this invention may be a polyester film, such as polyethyleneterphthalate (PET) or polyethylenenaphthalate (PEN), an acrylic film or a polycarbonate film. The post application adhesive layer may be an acrylic pressure sensitive adhesive or a polyester based adhesive.
- 30 Similarly, the laminating adhesive, when used, may be a

WO 02/077081

PCT/US02/08687

- 34 -

polyester or acrylic based adhesive. Of course, a laminated film product may have film substrates that differ in composition and the laminating adhesive and post application adhesive need not be the same. If a

5 protective coating is present it will generally be a polyacrylate coating, most preferably a UV curable polyacrylate coating which forms a hard scratch resistant coating. The preparation of film products having protective coatings is described in U.S. Patent No.

10 4,557,980, the entire disclosure of which is incorporated by reference herein. The amount of quaterrylenetetra-carboxylic diimide of formula I employed in the film product of this invention to achieve infrared absorbtion is that amount which is effective to inhibit

15 the transmission of infrared radiation through the film product.

The following Examples illustrate and do not limit or restrict the invention. Amounts and percentages are in

20 weight.

25 PREPARATION OF TERT-ALKYLPHENOXY-SUBSTITUTED
QUATERRYLIMIDES

Example 1

A mixture of 28.6g (20 mmol) of a 1:1 mixture of

30 N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-

WO 02/077081

PCT/US02/08687

- 35 -

hexabromoquaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexabromoquaterrylene-3,4:13,14-tetracarboxylic diimide, 32.2g of para-tert-octylphenol, 9.95g of potassium carbonate and 150ml of N-methylpyrrolidone was heated to 95°C for 10 h while stirring in a nitrogen atmosphere.

After cooling down to room temperature, the precipitated reaction product was filtered off directly, washed with a little N-methylpyrrolidone and subsequently washed with water to neutral run-off. For purification a column filtration with silica gel as stationary and methylene chloride as mobile phase was carried out. After removal of the solvent, the final product was dried at 100°C under reduced pressure.

This reaction led to the complete replacement of the halogen atoms by the tert-alkylphenoxy radicals.

The total yield was 31g (71%) of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide.

Example 2

A tert-alkylphenoxy-substituted quaterrylimide was prepared in a manner substantially similar to Example 1,

WO 02/077081

PCT/US02/08687

- 36 -

except that the potassium carbonate was replaced with 13.5g of potassium t-butoxide, the mixture included 200ml of N-methylpyrrolidone and was heated to 80°C for 4 h. The total yield was 28g (64%) of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide.

10

Example 3

Example 1 was repeated by reacting 28.6 g of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexabromoquaterylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexabromoquaterylene-3,4:13,14-tetracarboxylic diimide with 20.6 g of p-tert-octylphenol and 6.9 g of potassium carbonate.

20

This afforded 27.6 g of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-8,18-dibromo-1,6,11,16-tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-8,19-dibromo-1,6,11,16-tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide in the form of a dark green crystalline powder, which corresponds to a yield of 71%.

30 In addition, the N-methylpyrrolidone mother liquor was

WO 02/077081

PCT/US02/08687

- 37 -

diluted with four times the amount of a 1:1 mixture of methanol and water to afford 11 g (yield 25%) of the 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide of Example 1.

10. Example 4

38.7 g of the 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-8,18-dibromo-1,6,11,16-tetra(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-8,19-dibromo-1,6,11,16-tetra(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide were reacted with 10.7 g of p-tert-octylphenol and 3.32 g of potassium carbonate in 170 ml of N-methylpyrrolidone similarly to Example 1, except that the reaction time was extended to 18 h.

This afforded 39.5 g of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide in the form of a light green amorphous powder having a residual bromine content < 0.05% by weight, which corresponds to a yield of 90%.

WO 02/077081

PCT/US02/08687

- 38 -

Example 5

The 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-8,18-dibromo-1,6,11,16-

5 tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide and

N,N'-bis(2,6-diisopropylphenyl)-8,19-dibromo-1,6,11,16-tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide of Example 3 (hereinafter designated

10 "Ia") was converted by dehalogenation into

N,N'-bis(2,6-diisopropylphenyl)-1,6,11,16-

tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-

tetracarboxylic diimide. The dehalogenation was conducted according to the following methods:

15

a) A mixture of 38.7 g of Ia and 600 ml of N-methylpyrrolidone was stirred under nitrogen and heated to 130°C, admixed with 6.75 g of potassium tert-butoxide and maintained at 130°C for 1.5 h.

20

After cooling down to room temperature, the reaction product was precipitated by adding the reaction mixture to 2 liters of 5% by weight hydrochloric acid, filtered off, washed first with 5% by weight hydrochloric acid to

25 colorless run-off and then with water to neutral run-off

and dried at 100°C under reduced pressure. The isolated reaction product was then subjected to column chromatography over silica gel using 1:1 toluene/hexane as mobile phase.

30

WO 02/077081

PCT/US02/08687

- 39 -

This afforded 20.0 g of N,N'-bis(2,6-diisopropylphenyl)-1,6,11,16-tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide in the form of a light green amorphous powder
5 having a UV/VIS spectroscopic purity of > 99% and a residual bromine content < 0.01%, which corresponds to a yield of 56%.

b) Example 5a) was repeated, except that 4.1 g of
10 potassium carbonate was used as base instead of potassium tert-butoxide. The workup and purification were likewise carried out similarly to Example 5a). This afforded 18.6 g of N,N'-bis(2,6-diisopropylphenyl)-1,6,11,16-tetra(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic
15 diimide in the form of a light green amorphous powder having a purity of > 99.5% and a residual bromine content of 0.00%, which corresponds to a yield of 52%.

c) A mixture of 38.7 g of Ia, 3.8 g of sodium
20 borohydride, 0.46 g of tetrakis (triphenylphosphine)palladium(0) and 600 ml of dioxane was heated to 60°C for 48 h while stirring in a nitrogen atmosphere.

25 After cooling down to room temperature, excess hydride was decomposed by gradual addition of 10 ml of water. The rest of the workup and purification were carried out similarly to Example 5a.

30 This afforded 21.7 g of N,N'-bis(2,6-diisopropylphenyl)-

WO 02/077081

PCT/US02/08687

- 40 -

1,6,11,16-tetra(p-tert-octylphenoxy)quaterrylene-
3,4:13,14-tetracarboxylic diimide in the form of a light
green amorphous powder having a purity of > 99% and a
residual bromine content of 0.00%, which corresponds to a
5 yield of 61%.

d) A mixture of 38.7 g of Ia, 3.8 g of sodium
borohydride, 0.46 g of tetrakis
(triphenylphosphine)palladium (0) and 1000 ml of
10 acetonitrile was heated to 69°C for 27 hours while
stirring in a nitrogen atmosphere.

The rest of the workup and purification were carried out
similarly to Example 5c.

15

The yield was 29.1g (82%) of N,N'-bis(2,6-
diisopropylphenyl)-1,6,11,16-tetra(p-tert-
octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic
diimide with a purity of > 99% and a residual bromine
20 content of 0.00%

WO 02/077081

PCT/US02/08687

- 41 -

PREPARATION OF PVB SHEET CONTAINING QUATERRYLIMIDES

Example 6

- 5 The following were charged to a vessel which was then heated to 50°C and stirred for 1 hour.

	<u>Component</u>	<u>Amount (gm)</u>
10	N,N'-bis(2,6-diisopropylphenyl) quaterrylene-3,4:13,14-tetracarboxylic diimide IR-absorber	0.63
	triethyleneglycol di-2-ethylhexanoate	855
	Tinuvin benzotriazole derivative (UV absorber) from Ciba Geigy Co.	15.8
15	magnesium 2-ethyl butyrate	2.8g

Then 2250g PVB resin from Solutia Inc. as Butvar B-79 was added and stirring was continued for about one min. to form a premix slurry.

20

- The premix slurry was extruded using a Model KL-125 extruder (Killion Extruders, Inc.) with a single-screw configuration and a 1.25 inch (3.18 cm) screw diameter. The barrel temperature was maintained between 180 to 200°C. A seven inch (17.78 cm) wide slit die having a 0.029 inch (0.074 cm) gap and a die temperature of 190°C was used. As the polymer film exited the die it was quenched in a water bath at 14°C and was pulled by a roller which was speed controlled to result in a plasticized PVB interlayer sheet about 30 mil (0.76 mm) thick containing the quaterrylimide defined above

30

WO 02/077081

PCT/US02/08687

- 42 -

uniformly dispersed throughout the formulation of the sheet.

The plasticized PVB interlayer sheet was interposed
5 between 2 layers of clear float glass (PPG Industries, Inc.), each having a thickness of 2.1 mm, and the combination was placed in an autoclave where it was exposed to 135°C and 12 kg/cm² pressure for about 60 minutes to form a glass laminate having visible light
10 transmitting and infrared light absorbing properties.

Example 7

A PVB sheet and laminate thereof were prepared in a
15 manner similar to Example 6, except the quaterrylimide was replaced with 0.945 grams of a 1:1 mixture of N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide and N,N'-bis(2,6-diisopropylphenyl)-
20 1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterrylene-3,4:13,14-tetracarboxylic diimide.

Example 8

25 A PVB sheet and laminate thereof were prepared in a manner similar to Example 6, except the quaterrylimide was replaced with
1.575 grams of N,N'-bis(2,6-diisopropylphenyl)-
1,6,11,16-tetra(p-tert-octylphenoxy)quaterrylene-
30 3,4:13,14-tetracarboxylic diimide.

WO 02/077081

PCT/US02/08687

- 43 -

Example 9

A glass laminate was prepared in a manner similar to Example 7 except the interlayer was comprised of both a sheet of PVB containing the quaternarylimide as described in Example 7 in combination with a PVB sheet containing 100 nanometers or less doped metal oxide particles.

Ultrafine particles of antimony tin oxide were obtained from Sumitomo Osaka Cement Co. Ltd., 1 Mitoshirocho, Kanda, Chiyoda-Ku, Tokyo, Japan. These particles were $<0.1\mu\text{m}$, preferably $0.05\mu\text{m}$, diameter or less in size and are believed prepared according to working Example 1 of Japanese Laid-Open Patent Application (Kokai) No. 8-217500 dated August 27, 1996, of Sumitomo Osaka Cement, the disclosure of such Kokai being incorporated herein by reference. Antimony tin oxide powder of particle size $<0.05\mu\text{m}$ is also available from Nanophase Technologies Corp., 453 Commerce St., Burr Ridge, IL.

More particularly, as disclosed in the noted Kokai, antimony chloride (SbCl_3) and hydrated tin chloride ($\text{SnCl}_4 \cdot 5\text{H}_2\text{O}$) are dissolved in hydrochloric acid solution to which is then added 25% ammonia solution and the mixture allowed to react. The resulting sol-like dispersion is filtered and washed to remove ammonium chloride and in a sealed vessel heated to and kept at 350°C for 5 hours after which steam is released resulting in cooling and a concentration of the contents to 25% solids dispersion of antimony tin oxide with an average particle diameter of about $0.05\mu\text{m}$ (500\AA). Octadecylamine flocculant is added to the

WO 02/077081

PCT/US02/08687

- 44 -

dispersion to form a flocculated precipitate which is filtered and dried at 100°C for 2 hours to yield a powder which is tin oxide (SnO₂) doped with about 9-10 weight percent (wt.%) antimony oxide (Sb₂O₃),
5 hereinafter sometimes abbreviated ATO.

The ATO powder was mixed with and dispersed in toluene using an ultrasonic disperser. A minor amount (believed to be about 3 weight parts) of a 10% toluene
10 solution of an anionic surfactant was added to and thoroughly mixed with the dispersion of the ATO particles. The surfactant functions to prevent excess agglomeration of the ATO particles, which after incorporation into the formulation of the PVB sheet in
15 the absence of the surfactant could lead to excess undesirable haze in the finished glass laminates. 115 weight parts triethylene glycol di-2-ethyl hexanoate (3GEH) plasticizer was then added and the mixture was distilled under reduced pressure for 15 minutes at 95°C
20 to remove toluene. The liquid remaining is a 20% concentrate of ATO uniformly dispersed in 3GEH plasticizer.

The concentrate was further diluted with 3GEH to form a
25 0.8 wt.% diluted dispersion which was mixed with PVB resin from Solutia Inc. as Butvar B-79 and the other additives in amounts as follows:

19.152 gms	- diluted ATO dispersion
30 0.062 gms	- magnesium di-2-ethyl butyrate
50 gms	- PVB resin
0.173 gms	- Tinuvin UV absorber

WO 02/077081

PCT/US02/08687

- 45 -

A PVB sheet was compression molded from the above formulation and a four layer (glass-PVB-PVB-glass) glass laminate containing such sheet was formed.

- 5 The glass laminates of Examples 6-9 were tested according to the following procedures.

Results are in Table I following.

- 10 1) Visible Light Transmittance (Tv) - % light transmission over the visible wavelength range of 380 to 780 nanometers (nm) measured according to International Standards Organization (ISO) Designation 9050: 1990(E), in illuminant D65, 10 degree observer.
- 15 2) Solar Direct Transmittance (Ts) - % solar energy transmittance over the spectral range of 350 to 2100 nanometers measured according to ISO Designation 9050: 1990 (E) using Air Mass 2 solar spectral distribution.
- 20 3) Pummel Adhesion (no units) measures PVB sheet interlayer adhesion to glass. Prepare two ply glass laminates as recited above, condition to minus 17°C and manually pummel each with a 1 pound (454 g) hammer to
- 25 break the glass. Remove all broken glass unadhered to the PVB sheet. Visually compare glass left adhered to the sheet with a set of standards of known pummel scale, the higher the number of the standard, the more glass remaining adhered to the sheet - i.e. at pummel
- 30 zero no glass is adhered and at pummel 10 100% of the sheet surface is adhered. Desirable impact dissipation occurs at a pummel adhesion value of 3 to 7. At less

WO 02/077081

PCT/US02/08687

- 46 -

than 3 too much glass is lost whereas at more than 7 adhesion is generally too high and shock absorption poor.

- 5 4) Haze (%) - according to ASTM Designation D1003-97
- Procedure A using a hazemeter. Values < 3%
considered acceptable.

10

TABLE 1

Example	(Absorber conc.) (wt %)	TV	TS	Pummel Adhesion	Haze %
6	0.020	70	53	4	N/A
7	0.030	79	55	5	1.50
15 8	0.050	72	44	6	0.6
9	0.030/0.22*	71	43	5/8**	0.73

* concentration of quaterrylimide and ATO,
respectively

20

** pummel adhesion measured on each sheet

Example 10

25

A PVB sheet and laminate thereof are prepared in a manner similar to Example 6, except the quaterrylimide is replaced with 1.575 grams of N,N'-bis(2,6-diisopropylphenyl)tetra(4-tert-butylphenoxy) quaterrylene-3,4:13,14-tetracarboxylic diimide.

30

Example 11

A PVB sheet and laminate thereof are prepared in a

WO 02/077081

PCT/US02/08687

- 47 -

manner similar to Example 6, except the quaterrylimide is replaced with 0.63 grams of N,N'-bis(dodecyl) quaterrylene-3,4:13,14-tetracarboxylic diimide.

5 Example 12

A PVB sheet and laminate thereof are prepared in a manner similar to Example 6, except the quaterrylimide is replaced with 0.63 grams of N,N'-bis(cyclohexyl) quaterrylene-3,4:13,14-tetracarboxylic diimide.

COLORANTS ADDED TO A PVB SHEET CONTAINING
QUATERRYLIMIDES

Example 13

15 An IR absorbing dye was added to a PVB sheet that was prepared in a manner similar to Example 8, except that the IR absorber concentration was 0.032 wt.% of the total weight of the sheet. Pigments were also added. C.I. pigment blue 15 was added at a concentration of
20 0.00128 wt.% and C.I. pigment red was added at a concentration of 0.00038 wt.%. The concentrations are based upon the total weight of the sheet. A green color was produced by including the colorants. The green colored PVB sheet was placed between two clear
25 glass sheets forming a green colored laminate. Each clear glass sheet had a thickness in the range of 2.1 to 2.3 mm. Using the CIELAB System, the green colored laminate had L*, a*, and b* coordinates that were determined to be:

30 $L^* = 87.6$, $a^* = -20.0$, and $b^* = 2.0$.

WO 02/077081

PCT/US02/08687

- 48 -

Example 14

An IR absorbing dye was added to a PVB sheet that was prepared in a manner similar to Example 8, except that the IR absorber concentration was 0.0435 wt.% of the total weight of the sheet. Pigments were also added. C.I. pigment blue 15 was added at a concentration of 0.00315 wt.%, along with C.I. pigment red 209 at a concentration of 0.01867 wt.%, and carbon black at a concentration of 0.00050 wt.%. All concentrations are based upon the total weight of the sheet. A gray color was produced by including the colorants. The PVB sheet was placed between two clear glass sheets forming a gray colored laminate. Each clear glass sheet had a thickness in the range of 2.1 to 2.3 mm. Using the CIELAB System, the L*, a*, and b* coordinates were determined to be:

L* = 73.1, a* = -2.8, and b* = -3.8,
for the gray colored laminate.

20

The preceding description is for illustration and should not be taken as limiting. Various modifications and alterations will be readily suggested to persons skilled in the art. It is intended, therefore, that the foregoing be considered exemplary only and that the scope of the invention be ascertained from the following claims.


WO 02/077081

PCT/US02/08687

- 49 -

IN THE CLAIMS:

1. Plasticized polyvinyl butyral sheet containing an infrared-absorbing effective amount of at least one quaterrylenetetracarboxylic diimide infrared-absorbing additive dispersed therein of formula I:



wherein

R and R' are independently C_1 - C_{30} -alkyl whose carbon chain optionally is interrupted by one or more of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which optionally is monosubstituted or polysubstituted by cyano, C_1 - C_6 -alkoxy or a 5-, 6- or 7-membered heterocyclic radical which is attached via a nitrogen atom and which optionally contains additional heteroatoms and optionally is aromatic;

C_5 - C_8 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1 - C_6 -alkyl; or

aryl or hetaryl, each of which optionally is

WO 02/077081

PCT/US02/08687


- 50 -

monosubstituted or polysubstituted by C_1-C_{18} -alkyl, C_1-C_6 -alkoxy, cyano, $-CONHR^2$, $-NECOR^2$ and/or aryl- or hetarylazo, each of which optionally is substituted by C_1-C_{10} -alkyl, C_1-C_6 -alkoxy or halogen, where

R^1 is hydrogen or C_1-C_6 -alkyl; and

R^2 is hydrogen; C_1-C_{18} -alkyl; aryl or hetaryl, each of which optionally is substituted by C_1-C_6 -alkyl, C_1-C_6 -alkoxy, halogen or cyano;

X is independently halogen; C_1-C_{18} -alkyl, aryloxy, arylthio, hetaryloxy or hetarylthio, each of which may be substituted by C_1-C_4 alkyl, or C_1-C_{18} -alkoxy; or



where

R^3 is C_1-C_6 -alkyl, whose carbon chain may be interrupted by one or more groups selected from the group consisting of $-O-$, $-S-$, $-NR^1-$, $-CO-$ and/or $-SO_2-$ and which may be monosubstituted or polysubstituted by C_1-C_6 -alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic; or C_3-C_6 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of $-O-$, $-S-$, $-NR^1-$, $-CO-$ and/or $-SO_2-$ and which may be monosubstituted or


WO 02/077081

PCT/US02/08687


-51-

polysubstituted by C₁-C₆-alkyl;
and p is from 0-16.

2. The sheet of claim 1, wherein X is independently
chloro, bromo or



3. The sheet of claim 1, wherein X is



and p is 2-8.

4. The sheet of claim 1, wherein p is 0.

5. The sheet of claim 3, wherein R³ is selected from
the group consisting of:

methyl, ethyl, propyl, isopropyl, butyl, isobutyl,
tert-butyl, pentyl, isopentyl, neopentyl, hexyl, 2-
methylpentyl, tert-pentyl, heptyl, 1-ethylpentyl,
octyl, 2-ethylhexyl and isooctyl;

2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-
isopropoxyethyl, 2-butoxyethyl, 2- and 3-methoxypropyl,
2- and 3-ethoxypropyl, 2- and 3-propoxypropyl, 2- and
3-butoxypropyl, 2- and 4-methoxybutyl, 2- and 4-

WO 02/077081

PCT/US02/08687

- 52 -

ethoxybutyl, 2- and 4-propoxybutyl, 3,6-dioxaheptyl, 3,6-dioxaoctyl, 4,8-dioxanonyl, 3,7-dioxaoctyl, 3,7-dioxanonyl, 4,7-dioxaoctyl, 4,7-dioxanonyl, 2- and 4-butoxybutyl, 4,8-dioxadecyl, 3,6,9-trioxadecyl and 3,6,9-trioxaundecyl;

2-methylthioethyl, 2-ethylthioethyl, 2-propylthioethyl, 2-isopropylthioethyl, 2-butylthioethyl, 2- and 3-methylthiopropyl, 2- and 3-ethylthiopropyl, 2- and 3-propylthiopropyl, 2- and 3-butylthiopropyl, 2- and 4-methylthiobutyl, 2- and 4-ethylthiobutyl, 2- and 4-propylthiobutyl, 3,6-dithiaheptyl, 3,6-dithiaoctyl, 4,8-dithianonyl, 3,7-dithiaoctyl, 3,7-dithianonyl, 4,7-dithiaoctyl, 4,7-dithianonyl, 2- and 4-butylthiobutyl, 4,8-dithiadecyl, 3,6,9-trithiadecyl and 3,6,9-trithiaundecyl;

2-monomethyl- and 2-monoethylaminoethyl, 2-dimethylaminoethyl, 2- and 3-dimethylaminopropyl, 3-monoisopropylaminopropyl, 2- and 4-monopropylaminobutyl, 2- and 4-monomethylaminobutyl, 6-methyl-3,6-diazaheptyl, 3,6-dimethyl-3,6-diazaheptyl, 3,6-diazaoctyl, 3,6-dimethyl-3,6-diazaoctyl, 9-methyl-3,6,9-triazadecyl, 3,6,9-trimethyl-3,6,9-triazadecyl, 3,6,9-triazaundecyl and 3,6,9-trimethyl-3,6,9-triazaundecyl;

propan-2-on-1-yl, butan-3-on-1-yl, butan-3-on-2-yl and 2-ethylpentan-3-on-1-yl;

2-methylsulfonyl-ethyl, 2-ethylsulfonyl-ethyl, 2-propylsulfonyl-ethyl, 2-isopropylsulfonyl-ethyl, 2-

WO 02/077081

PCT/US02/08687

- 53 -

butylsulfonyl, 2- and 3-methylsulfonylpropyl, 2- and 3-ethylsulfonylpropyl, 2- and 3-propylsulfonylpropyl, 2- and 3-butylsulfonylpropyl, 2- and 4-methylsulfonylbutyl, 2- and 4-ethylsulfonylbutyl, 2- and 4-propylsulfonylbutyl and 4-butylsulfonylbutyl;

methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, sec-butoxy, tert-butoxy, pentoxy, isopentoxy, neopentoxy, tert-pentoxy and hexoxy;

cyclopentyl, 2- and 3-methylcyclopentyl, 2- and 3-ethylcyclopentyl, cyclohexyl, 2-, 3- and 4-methylcyclohexyl, 2-, 3- and 4-ethylcyclohexyl, 3- and 4-propylcyclohexyl, 3- and 4-isopropylcyclohexyl, 3- and 4-butylcyclohexyl, 3- and 4-sec-butylcyclohexyl, 3- and 4-tert-butylcyclohexyl, cycloheptyl, 2-, 3- and 4-methylcycloheptyl, 2-, 3- and 4-ethylcycloheptyl, 3- and 4-propylcycloheptyl, 3- and 4-isopropylcycloheptyl, 3- and 4-butylcycloheptyl, 3- and 4-sec-butylcycloheptyl, 3- and 4-tert-butylcycloheptyl, cyclooctyl, 2-, 3-, 4- and 5-methylcyclooctyl, 2-, 3-, 4- and 5-ethylcyclooctyl, 3-, 4- and 5-propylcyclooctyl, 2-dioxanyl, 4-morpholinyl, 2- and 3-tetrahydrofuryl, 1-, 2- and 3-pyrrolidinyl and 1-, 2-, 3- and 4-piperidyl.

6. The sheet of claim 3, wherein R³ is selected from the group consisting of methyl, ethyl, propyl, n-butyl, tert-butyl, cyclopentyl, cyclohexyl, cycloheptyl, 4-morpholinyl or mixtures thereof.

7. The sheet of claim 5, wherein R and R' are

WO 02/077081

PCT/US02/08687

- 54 -

independently selected from the group consisting of:

C₆-C₃₀-alkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C₁-C₆-alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic;

C₃-C₈-cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C₁-C₆-alkyl; and

aryl or hetaryl which may be monosubstituted or polysubstituted by C₁-C₁₈-alkyl, C₁-C₆-alkoxy, cyano, -CONH-R¹ and/or -NH-COR¹.

8. The sheet of claim 1, wherein R is 2,6-diisopropylphenyl.

9. The sheet of claim 1, wherein said sheet is further comprised of an infrared-absorbing effective amount of an inorganic infrared-absorbing additive.

10. The sheet of claim 1, wherein said sheet further comprises an ultraviolet light stabilizer.

11. The sheet of claim 1, wherein said sheet further comprises a colorant.

WO 02/077081


PCT/US02/08687

- 55 -

12. The sheet of claim 1, wherein said sheet exhibits a color selected from the group consisting of green and gray,

wherein said green color is defined by the CIELAB system, having an L* value from about 76.0 to about 94.0, an a* value from about -38.0 to about -8.0, and a b* value from about -5.0 to about 7.0, and wherein said gray color is defined by the CIELAB system, having an L* value from about 59.0 to about 87.0, an a* value from about -7.0 to about 3.0, and a b* value from about -8.0 to about 2.0.

13. Plasticized polyvinyl butyral sheet containing an infrared-absorbing effective amount of at least one tert-alkyphenoxy-substituted quaterrylenetetra-carboxylic diimide infrared absorbing additive dispersed therein of formula II:



where

Q is a N,N'-disubstituted quaterylene-3,4:13,14-tetracarboxylic diimide radical;

R³ is C₁-C₈-alkyl, whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or

WO 02/077081

PCT/US02/08687

- 56 -

polysubstituted by C₁-C₈-alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic; or C₅-C₈-cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C₁-C₈-alkyl;

Hal is chloro and/or bromo;

m is from 0 to 15; and

n is from 1 to 16, subject to the proviso that the sum m + n is ≤ 16.

14. The sheet of claim 13, wherein said sheet exhibits a color selected from the group consisting of green and gray,

wherein said green color is defined by the CIELAB system, having an L* value from about 76.0 to about 94.0, an a* value from about -38.0 to about -8.0, and a b* value from about -5.0 to about 7.0, and wherein said gray color is defined by the CIELAB system, having an L* value from about 59.0 to about 87.0, an a* value from about -7.0 to about 3.0, and a b* value from about -8.0 to about 2.0.


15. A multilayered plasticized polyvinyl butyral sheet having (a) a first sheet containing an infrared-absorbing effective amount of at least one

WO 02/077081

PCT/US02/08687

- 57 -

quaterrylenetetracarboxylic diimide infrared absorbing additive dispersed therein of formula I:



wherein

R and R' are independently C_1 - C_{30} -alkyl whose carbon chain optionally is interrupted by one or more of -O-, -S-, $-NR^1$ -, -CO- and/or $-SO_2$ - and which optionally is monosubstituted or polysubstituted by cyano, C_1 - C_6 -alkoxy or a 5-, 6- or 7-membered heterocyclic radical which is attached via a nitrogen atom and which optionally contains additional heteroatoms and optionally is aromatic;

C_3 - C_6 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, $-NR^1$ -, -CO- and/or $-SO_2$ - and which may be monosubstituted or polysubstituted by C_1 - C_6 -alkyl; or

aryl or hetaryl, each of which optionally is monosubstituted or polysubstituted by C_1 - C_{18} -alkyl, C_1 - C_6 -alkoxy, cyano, $-CONHR^2$, $-NHCOR^2$ and/or aryl- or hetarylazo, each of which optionally is substituted by

WO 02/077081

PCT/US02/08687


- 58 -

C_1-C_{18} -alkyl, C_1-C_6 -alkoxy or halogen, where

R^1 is hydrogen or C_1-C_6 -alkyl; and

R^2 is hydrogen, C_1-C_{18} -alkyl; aryl or hetaryl, each of which optionally is substituted by C_1-C_6 -alkyl, C_1-C_6 -alkoxy, halogen or cyano;

X is independently halogen; C_1-C_{18} -alkyl, aryloxy, arylthio, hetaryloxy or hetarylthio, each of which may be substituted by C_1-C_4 -alkyl, or C_1-C_{18} -alkoxy; or



where

R^3 is C_1-C_8 -alkyl; whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1-C_6 -alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic; or

C_5-C_8 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1-C_6 -alkyl;

and p is from 0-16; and

WO 02/077081

PCT/US02/08687

- 59 -

b) a second sheet having an infrared-absorbing effective amount of an inorganic infrared-absorbing additive.

16. The sheet of claim 15, wherein said sheet exhibits a color selected from the group consisting of: green and gray,

wherein said green color is defined by the CIELAB system, having an L* value from about 76.0 to about 94.0, an a* value from about -38.0 to about -8.0, and a b* value from about -5.0 to about 7.0, and wherein said gray color is defined by the CIELAB system, having an L* value from about 59.0 to about 87.0, an a* value from about -7.0 to about 3.0, and a b* value from about -8.0 to about 2.0.


17. The sheet of claim 15, wherein the inorganic infrared-absorbing additive is lanthanum hexaboride.

18. A laminate having visible light transmitting and infrared light absorbing properties comprising two glass sheets with a plasticized polyvinyl butyral sheet between the sheets of glass, said plasticized polyvinyl butyral sheet containing an infrared-absorbing effective amount of at least one quaternary tetra-carboxylic diimide infrared-absorbing additive dispersed therein of formula I:

WO 02/077081

PCT/US02/03687

- 60 -



wherein

R and R' are independently C₁-C₃₀-alkyl whose carbon chain optionally is interrupted by one or more of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which optionally is monosubstituted or polysubstituted by cyano, C₁-C₆-alkoxy or a 5-, 6- or 7-membered heterocyclic radical which is attached via a nitrogen atom and which optionally contains additional heteroatoms and optionally is aromatic;

C₃-C₈-cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C₁-C₆-alkyl; or

aryl or hetaryl, each of which optionally is monosubstituted or polysubstituted by C₁-C₁₈-alkyl, C₁-C₆-alkoxy, cyano, -CONR², -NHCOR² and/or aryl- or hetarylazo, each of which optionally is substituted by C₁-C₁₀-alkyl, C₁-C₆-alkoxy or halogen, where

WO 02/077081


PCT/US02/08687

- 61 -

R^1 is hydrogen or C_1-C_6 -alkyl; and

R^2 is hydrogen; C_1-C_{18} -alkyl; aryl or hetaryl, each of which optionally is substituted by C_1-C_6 -alkyl, C_1-C_6 -alkoxy, halogen or cyano;

X is independently halogen; C_1-C_{18} -alkyl, aryloxy, arylthio, hetaryloxy or hetarylthio, each of which may be substituted by C_1-C_4 -alkyl, or C_1-C_{18} -alkoxy; or



where

R^3 is C_1-C_8 -alkyl, whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1-C_6 -alkoxy or by a 5- to 7-membered heterocyclic radical which is attached via a nitrogen atom and may contain further heteroatoms and be aromatic; or C_5-C_8 -cycloalkyl whose carbon chain may be interrupted by one or more groups selected from the group consisting of -O-, -S-, -NR¹-, -CO- and/or -SO₂- and which may be monosubstituted or polysubstituted by C_1-C_6 -alkyl;

and p is from 0-16.

19. The laminate of claim 18, wherein said laminate exhibits a color selected from the group consisting of:

WO 02/077081

PCT/US02/08687

-62-

green and gray,
wherein said green color is defined by the CIELAB system, having an L* value from about 76.0 to about 94.0, an a* value from about -38.0 to about -8.0, and a b* value from about -5.0 to about 7.0, and
wherein said gray color is defined by the CIELAB system, having an L* value from about 59.0 to about 87.0, an a* value from about -7.0 to about 3.0, and a b* value from about -8.0 to about 2.0.

20. The laminate of claim 18, having a plasticized polyvinyl butyral sheet thickness of about 0.76 mm, more than 70% visible light transmittance and less than 45% direct solar transmittance measured according to ISO designation 9050:1990 (E) using Air Mass 2 solar spectral distribution.

21. The laminate of claim 18, further comprising a second sheet of plasticized polyvinyl butyral sheet disposed between said sheets of glass, wherein said second sheet of plasticized polyvinyl butyral sheet contains an infrared-absorbing effective amount of at least one inorganic infrared-absorbing additive.

22. The laminate of claim 21, wherein the inorganic infrared-absorbing additive is lanthanum hexaboride.

23. The laminate of claim 18, wherein at least one of said glass sheets is an infrared absorbing glass sheet.

24. The laminate of claim 18, further comprising a second sheet of plasticized polyvinyl butyral sheet

WO 02/077081

PCT/US02/08687

- 63 -

disposed between said sheets of glass and an infrared reflective layer disposed between said sheets of plasticized polyvinyl butyral.

25. The laminate of claim 18, wherein at least one of said glass sheets is an infrared reflective coated glass.

26. Plasticized polyvinyl butyral sheet containing an infrared-absorbing effective amount of at least one tert-alkylphenoxy-substituted quaterylene tetracarboxylic diimide infrared absorbing additive selected from the group consisting of N,N'-bis(2,6-diisopropylphenyl)-1,6,11,16-tetra(p-tert-octylphenoxy) quaterylene-3,4:13,14-tetracarboxylic diimide, N,N'-bis(2,6-diisopropylphenyl)-1,6,11,16-tetraphenoxyquaterylene-3,4:13,14-tetracarboxylic diimide, N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,19-hexa(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide, N,N'-bis(2,6-diisopropylphenyl)-1,6,8,11,16,18-hexa(p-tert-octylphenoxy)quaterylene-3,4:13,14-tetracarboxylic diimide or a mixture thereof.

27. The sheet of claim 26, wherein said sheet exhibits a color selected from the group consisting of: green and gray, wherein said green color is defined by the CIELAB system, having an L* value from about 76.0 to about 94.0, an a* value from about -38.0 to about -8.0, and a b* value from about -5.0 to about 7.0, and wherein said gray color is defined by the CIELAB

WO 02/077081


PCT/US02/08687

- 64 -

system, having an L^* value from about 59.0 to about 87.0, an a^* value from about -7.0 to about 3.0, and a b^* value from about -8.0 to about 2.0.

WO 02/077081

PCT/US02/08687



1 of 1

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/08687

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08J5/18 C08K5/3437 C08L29/14 C09B5/62

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08K C08L C09B C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPQ-Internal, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 986 099 A (MUELLEN KLAUS ET AL) 16 November 1999 (1999-11-16) cited in the application claim 1	1,2,4,8, 13,18
Y	DATABASE WPI Section Ch, Week 198441 Derwent Publications Ltd., London, GB; Class A14, AN 1984-253016 XP002207225 & JP 59 152249 A (TEIJIN LTD), 30 August 1984 (1984-08-30) abstract	1,2,4,8, 13,18
A	DE 199 40 708 A (BASF AG) 1 March 2001 (2001-03-01) claims 1,8	1-27

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the International filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition, or other means

P document published prior to the International filing date but later than the priority date claimed

T later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

A document member of the same patent family

Date of the actual completion of the International search

23 July 2002

Date of mailing of the International search report

09/08/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 apo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rose, E

International Application No

PCT/US 02/08687

Q.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>QUANTÉ H ET AL: "QUATERRYLENEBIS(DICARBOXIMIDES)" ANGEWANDTE CHEMIE. INTERNATIONAL EDITION, VERLAG CHEMIE. WEINHEIM, DE, vol. 34, no. 12, 7 July 1995 (1995-07-07), pages 1323-1325, XP002002793 ISSN: 0570-0833 column 1, line 5-23 figure 14</p>	1,2,4,8, 13,18
Y	<p>PATENT ABSTRACTS OF JAPAN vol. 017, no. 659 (C-1137), 7 December 1993 (1993-12-07) & JP 05 213637 A (NISSAN MOTOR CO LTD; OTHERS: 01), 24 August 1993 (1993-08-24) abstract</p>	1,2,4,8, 13,18
A	<p>US 5 405 962 A (MUELLEN KLAUS ET AL) 11 April 1995 (1995-04-11) cited in the application claim 1 column 4, line 13-15</p>	1-27
A	<p>WO 00 52099 A (CIBA SC HOLDING AG) 8 September 2000 (2000-09-08) claims 1-5</p>	1-27
P,A	<p>WO 01 43963 A (SOLUTIA INC.) 21 June 2001 (2001-06-21) claim 1</p>	1-27

Source: PCT/US 02/08687 (Continuation of international application No. 02/08687)

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/08687

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5986099	A	16-11-1999	CN 1169155 A	31-12-1997
			DE 59601770 D1	02-06-1999
			WO 9622332 A1	25-07-1996
			EP 0804507 A1	05-11-1997
			FI 973056 A	18-07-1997
			JP 11502546 T	02-03-1999
			US 6124458 A	26-09-2000
JP 59152249	A	30-08-1984	NONE	
DE 19940708	A	01-03-2001	DE 19940708 A1	01-03-2001
			WO 0116109 A1	08-03-2001
			EP 1206456 A1	22-05-2002
JP 05213637	A	24-08-1993	NONE	
US 5405962	A	11-04-1995	DE 4236885 A1	05-05-1994
			DE 59303358 D1	05-09-1996
			EP 0596292 A1	11-05-1994
			JP 6263994 A	20-09-1994
WO 0052099	A	08-09-2000	AU 3154800 A	21-09-2000
			WO 0052099 A1	08-09-2000
WO 0143963	A	21-06-2001	AU 2261301 A	25-06-2001
			WO 0143963 A1	21-06-2001

PTO/SB/97 (08-04)

Approved for use through 07/31/2008. OMB 0651-0031

U. S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Application No. (if known): 10/559,874

Attorney Docket No.: 21581-00462-US

Certificate of Transmisslon under 37 CFR 1.8

I hereby certify that this correspondence is being facsimile transmitted to the United States Patent and Trademark Office.

on October 27, 2009
Date


Signature

Pam Rollins-Butler

Typed or printed name of person signing Certificate

N/A

Registration Number, if applicable

(202) 331-7111

Telephone Number

Note: Each paper must have its own certificate of transmlaeson, or this certificate must identify each submitted paper.

*** RX REPORT ***

RECEPTION OK

TX/RX NO	6060
RECIPIENT ADDRESS	202 331 7111
DESTINATION ID	
ST. TIME	10/27 11:55
TIME USE	22'45
PGS.	100
RESULT	OK